


PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 23/04, 21/08, 35/10, C07C 57/04, 51/353, 51/347, 51/09, 67/343, 69/54		A1	(11) International Publication Number: WO 99/52628 (43) International Publication Date: 21 October 1999 (21.10.99)
(21) International Application Number: PCT/GB99/01029 (22) International Filing Date: 1 April 1999 (01.04.99) (30) Priority Data: 9807498.2 8 April 1998 (08.04.98) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): JACKSON, Samuel, David [GB/GB]; 62 The Headlands, Darlington, County Durham DL3 8RP (GB). JOHNSON, David, William [GB/GB]; Crown Cottage, Knayton, Thirsk, North Yorkshire YO7 4AS (GB). SCOTT, John, David [GB/GB]; 3 Lindsay Walk, Cuddington, N. Northwich, Cheshire CW8 2YQ (GB). KELLY, Gordon, James [GB/GB]; 26 Troon Avenue, Darlington, Co Durham DL1 3HY (GB). WILLIAMS, Brian, Peter [GB/GB]; 24 Shays Drive, Clitheroe, Lancashire BB7 1LL (GB). (74) Agents: GIBSON, Sara, Hillary, Margaret et al.; ICI Group Intellectual Property, P.O. Box 90, Wilton, Middlesbrough, Cleveland TS90 8JE (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report. 	
(54) Title: PRODUCTION OF UNSATURATED ACIDS OR ESTERS THEREOF AND CATALYSTS THEREFOR			
(57) Abstract <p>The production of ethylenically unsaturated acids or esters by the catalytic reaction of an alkanoic acid or ester, especially methyl propionate, with formaldehyde, and a catalyst therefor wherein the catalyst comprises <u>a porous high surface area silica containing 1-10 % by weight of an alkali metal, especially cesium</u>, (expressed as metal) and having compounds of at least one <u>modifier element</u> selected from boron, magnesium, aluminium, zirconium and hafnium dispersed in the pores of said silica in such amount that the catalyst contains a total of 0.25 to 2 gram atoms of primary modifier element per 100 moles of silica.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.


AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Production of unsaturated acids or esters thereof and catalysts therefor

This invention relates to the production of ethylenically unsaturated acids or esters thereof, particularly methacrylic acid or alkyl methacrylates, and in particular to novel catalysts therefor.

Such acids or esters may be made by reacting an alkanolic acid (or ester) of the formula

- 5 R' - CH₂ - COOR, where R and R' are each, independently, hydrogen or an alkyl group, especially a lower alkyl group containing for example 1-4 carbon atoms, with formaldehyde. Thus methacrylic acid or alkyl esters thereof, especially methyl methacrylate, may be made by the catalytic reaction of propionic acid, or the corresponding alkyl ester, e.g. methyl propionate, with formaldehyde in accordance with the reaction sequence:



The reaction is typically effected at an elevated temperature, usually in the range 250-400°C, using a basic catalyst. Where the desired product is an ester, the reaction is preferably effected in the presence of the relevant alcohol in order to minimise the formation of the corresponding acid

- 15 through hydrolysis of the ester. Also for convenience it is often desirable to introduce the formaldehyde in the form of formalin. Hence for the production of methyl methacrylate, the reaction mixture fed to the catalyst will generally consist of methyl propionate, methanol, formaldehyde and water.

- 20 Suitable catalysts that have been used include alkali metal-doped, especially cesium-doped, silica catalysts. It has been found that certain cesium-doped silica catalysts, i.e. those based upon gel silicas, have an unacceptable service life as they lose their activity and selectivity in a relatively short time. This activity loss may be attributed to two factors.

- Firstly the alkali metal compound employed may exhibit appreciable volatility under the reaction conditions employed and so there may be a loss of activity through loss of alkali metal. As described in US 4 990 662, this may be overcome by incorporating a suitable alkali metal compound into the process gas stream so that alkali metal compound is deposited on the catalyst during operation to compensate for any alkali metal compound lost through volatilisation.

- Secondly, as may be inferred from US 4 942 258, it is believed that for the alkali metal to be active, the support should have a certain minimum surface area. The requisite area is dependent on the amount of alkali metal in the catalyst: thus it may be inferred that there is a minimum surface area required per unit of alkali metal. During operation, there is a tendency for the silica support to lose surface area. Thus under the reaction conditions there is a risk of hydrolysis of the silica, not only by the water produced by the reaction, but also from water present in the reaction mixture, for example resulting from introduction of the formaldehyde as formalin. We have found that the loss of

performance of the gel silica catalysts with time largely results from such hydrolysis causing a decrease in the surface area of the catalyst with time.

Typically the catalyst contains 1-10% by weight of the alkali metal. Preferably at least 2% by weight of alkali metal is employed so that the process can be operated at sufficiently low
5 temperatures that loss of alkali metal through volatilisation can be minimised. The operation at low temperatures has the additional advantage that the rate of deposition of coke, which tends to block the pores of the silica and so reduce activity, is decreased.

We have found that the incorporation of certain modifiers, such as compounds of elements such as boron, aluminium, magnesium, zirconium, or hafnium into the catalysts, in addition to the
10 alkali metal, retards the rate of surface area decrease. In the catalysts of the invention, it is important that the modifier is intimately dispersed in the silica, rather than simply being in the form of particles mixed with the silica particles. It is probable that the metal compounds in whatever form they are added will convert to oxides or (particularly at the surface of the silica) hydroxides before or during drying, calcination or operation of the catalyst and interact either on the surface or in the bulk
15 of the silica structure in that form. Furthermore it is important that the amount of modifier is within certain limits: if there is too little modifier, no significant advantage accrues while if too much modifier is employed the selectivity of the catalyst may be adversely affected. Generally the amount of modifier required is in the range 0.25 to 2 gram atoms of the modifier element per 100 moles of silica.

20 The aforesaid US 4 990 662 indicates that silicas may contain materials such as aluminium, zirconium, titanium, and iron compounds as trace impurities. That reference however indicates that improved catalysts are obtained if such impurities are removed by acid extraction to give a trace impurity content below 100 ppm.

EP 0 265 964 discloses the use of silica supported catalysts containing antimony as well as
25 the alkali metal. The description indicates that the alumina content is desirably less than 500 ppm. A comparative, antimony-free, example discloses the use of a composition containing 950 ppm alumina. This corresponds to 0.11 gram atoms of aluminium per 100 moles of silica.

US 3 933 888 discloses the production of methyl methacrylate by the above reaction using a catalyst formed by calcining a pyrogenic silica with a base such as a cesium compound, and
30 indicates that the pyrogenic silica may be mixed with 1-10% by weight of pyrogenic zirconia. That reference also discloses the use of a catalyst made from a composition containing cesium as the alkali metal and a small amount of borax. The amount of boron however is about 0.04 gram atoms per 100 moles of silica and so is too small to have any significant stabilising effect. DE 2 349 054 C, which is nominally equivalent to US 3 933 888, exemplifies catalysts containing zirconia or hafnia
35 in admixture with the silica: the results quoted indicate that the zirconia or hafnia containing catalysts give a lower yield based upon the amount of formaldehyde employed.

Yoo discloses in "Applied Catalysis", 102, (1993) pages 215-232 catalysts of cesium supported on silica doped with various modifiers. While bismuth appeared to be a satisfactory dopant, catalysts doped with lanthanum, lead or thallium gave short term improvements. However high levels of lanthanum gave products of low selectivity while low levels of lanthanum gave catalysts that sintered much faster than the bismuth doped catalysts. The effective additives were all highly toxic heavy metals with appreciable volatility: these considerations preclude their use as catalyst components.

The aforementioned US 3 933 888 indicated that it was important to use a pyrogenic silica and showed that other types of silicas were unsuitable. The pyrogenic silicas said to be suitable are those having a total surface area in the range 150-300 m²/g, a total pore volume of 3-15 cm³/g and a specified pore size distribution wherein at least 50% of the pore content is in the form of pores of diameter above 10000 Å (1000 nm) and less than 30% is in the form of pores of diameter below 1000 Å (100 nm). In contrast, in the present invention the silicas that may be employed are preferably porous high surface area silicas such as gel silicas, precipitated gel silicas and agglomerated pyrogenic silicas.

Accordingly the present invention provides a catalyst comprising a porous high surface area silica containing 1-10% by weight of an alkali metal (expressed as metal), wherein the catalyst contains a compound of at least one modifier element selected from boron, magnesium, aluminium, zirconium and hafnium in such amount that the catalyst contains a total of 0.25 to 2 gram atoms of said modifier element per 100 moles of silica, said modifier element compound being dispersed in the pores of said silica.

The silica employed in the invention preferably has a surface area of at least 50 m²g⁻¹. The surface area may be measured by well known methods, a preferred method being a standard BET nitrogen absorption method as is well known in the art. Preferably the bulk of the surface area of the silica is present in pores of diameter in the range 5-150 nm. Preferably the bulk of the pore volume of the silica is provided by pores of diameter in the range 5-150 nm. By "the bulk" of its pore volume or surface area is provided by pores of diameter in the range 5-150 nm we mean that at least 50% of the pore volume or surface area is provided by pores of this diameter and more preferably at least 70%.

Preferred alkali metals are potassium, rubidium, or especially cesium. The alkali metal content is preferably in the range 3-8%, by weight (expressed as metal).

Gel silicas are preferred although suitable pyrogenic silicas may also be used.

The preferred modifier elements are zirconium, aluminium or boron.

The invention also provides a process for the manufacture of ethylenically unsaturated acids or esters thereof, particularly methacrylic acid or alkyl methacrylates, by reaction of an alkanolic acid, or ester of an alkanolic acid, of the formula R' - CH₂ - COOR, where R and R' are each,

independently, hydrogen or an alkyl group, especially a lower alkyl group containing for example 1-4 carbon atoms, with formaldehyde in the presence of a catalyst as aforesaid.

The process is particularly suitable for the manufacture of methacrylic acid or especially methyl methacrylate, in which cases the alkanolic acid or ester is propionic acid or methyl propionate respectively.

Mixtures of modifier elements may be used, for example aluminium and zirconium, or magnesium and zirconium. The total amount of the modifier element in the catalyst is preferably in the range 0.25 to 1.5 gram atoms per 100 moles of silica. Too little modifier element generally results in inadequate stabilisation of the silica support, leading to loss of activity through loss of surface area, while too much modifier element often leads to a decrease in the selectivity of the catalyst.

The catalysts may be made by impregnating silica particles of the physical dimensions required of the catalyst with a solutions of a suitable compounds, e.g. salts, of the modifier element in a suitable solvent, followed by drying. The impregnation and drying procedure may be repeated more than once in order to achieve the desired additive loading. As there appears to be competition between the modifier and alkali metal for active sites on the silica, it may be desirable for the modifier to be incorporated before the alkali metal. We have found that multiple impregnations with aqueous solutions tend to reduce the strength of the catalyst particles if the particles are fully dried between impregnations and it is therefore preferable in these cases to allow some moisture to be retained in the catalyst between successive impregnations. When using non-aqueous solutions, it may be preferable to introduce the modifier first by one or more impregnations with a suitable non-aqueous solution, e.g. a solution of an alkoxide or acetate of the modifier metal in ethanol, followed by drying and then the alkali metal may be incorporated by a similar procedure using a solution of a suitable alkali metal compound. Where aqueous solutions are employed, it is preferable to effect the impregnation using an aqueous solution of e.g. nitrates or acetates of the modifier metal and cesium of sufficient concentration that the desired loading of modifier and cesium is effected in a single step, followed by drying.

The modifier elements may be introduced into the silica particles as soluble salts but we believe that the modifier element(s) are present in the silica in the form of oxides and /or hydroxides (especially at the surface of the silica) which are formed by ion exchange during impregnation, drying, calcining or catalytic use of the catalyst.

Alternatively the modifier may be incorporated into the composition by co-gelling or co-precipitating a compound of the modifier element with the silica, or by hydrolysis of a mixture of the modifier element halide with a silicon halide. Methods of preparing mixed oxides of silica and zirconia by sol gel processing are described by Bosman et al in J Catalysis Vol 148 (1994) page 660 and by Monros et al in J Materials Science Vol 28, (1993), page 5832. Doping of silica

spheres with boron during gelation from tetraethyl orthosilicate (TEOS) is described by Jubb and Bowen in J Material Science, volume 22, (1987), pages 1963-1970. Methods of preparing porous silicas are described in Iler R K, The Chemistry of Silica, (Wiley, New York, 1979), and in Brinker C J & Scherer G W "Sol-Gel Science" published by Academic Press (1990). Thus methods of
5 preparing suitable silicas are known in the art.

The catalysts are then preferably calcined, for example in air, at a temperature in the range 300 to 600°C, particularly at 400-500°C before use, although we have found that this may not always be necessary.

The catalysts will normally be used in the form of a fixed bed and so it is desirable that the
10 composition is formed into shaped units, e.g. spheres, granules, pellets, aggregates, or extrudates, typically having maximum and minimum dimensions in the range 1 to 10 mm. Where an impregnation technique is employed, the silica may be so shaped prior to impregnation. Alternatively the composition may be so shaped at any suitable stage in the production of the catalyst. The catalysts are also effective in other forms, e.g. powders or small beads and may be
15 used in this form.

The alkanolic acid or ester thereof and formaldehyde can be fed, independently or after prior mixing, to the reactor containing the catalyst at molar ratios of acid or ester to formaldehyde of from 20:1 to 1:20 and at a temperature of 250-400°C with a residence time of 1-100 seconds and at a pressure of 1-10 bara. Water may be present up to 60% by weight of the reaction mixture, although
20 this is preferably minimised due to its negative effect both on catalyst decay and hydrolysis of esters to acids. Formaldehyde can be added from any suitable source. These include but are not limited to aqueous formaldehyde solutions, anhydrous formaldehyde derived from a formaldehyde drying procedure, trioxane, diether of methylene glycol and paraformaldehyde. Where forms of formaldehyde which are not as free or weakly complexed formaldehyde are used, the formaldehyde
25 will form in situ in the synthesis reactor or in a separate reactor prior to the synthesis reactor. Thus for example, trioxane may be decomposed over an inert material or in an empty tube at temperatures over 350°C or over an acid catalyst at over 100°C. As a second example, methylal may be decomposed by reaction with water to form formaldehyde and methanol or without water to form dimethyl ether and formaldehyde. This can be accomplished either within the reactor or in a
30 separate reactor containing a catalyst such as an heterogeneous acid catalyst. In this case it is advantageous to feed the alkanolic acid or ester thereof ester separately to the synthesis reactor to prevent its decomposition over the acid catalyst.

When the desired product is an unsaturated ester made by reacting an ester of an alkanolic acid ester with formaldehyde, the alcohol corresponding to the ester may also be fed to the reactor
35 either with or separately to the other components. The alcohol, amongst other effects, reduces the quantity of acids leaving the reactor. It is not necessary that the alcohol is added at the beginning

of the reactor and it may for instance be added in the middle or near the back, in order to effect the conversion of acids such as propionic acid, methacrylic acid to their respective esters without depressing catalyst activity.

Other additives may be added either as inert diluents to reduce the intensity of the reaction or to control heat evolution from the catalyst as a result of reaction. Reaction modifiers may also be added, to for instance change the rate of carbon laydown on the catalyst. Thus for instance oxidising agents such as oxygen may be added at low levels to reduce the rate of coke formation. Additives may also be included to aid separations by for instance changing the composition of an azeotrope. Whilst such components to achieve the latter effect may be advantageously added after the reactor, in some circumstances it may be advantageous to include the additive in the reactor.

In order to minimise the loss of alkali metal through volatilisation, alkali metal, in a suitable form, e.g. a volatile salt, may be continuously or intermittently fed to the reactor.

The invention is illustrated by the following examples.

Examples 1-4

In these examples the silica employed was a gel silica in the form of spheres of diameter in the range 2-4 mm having a purity of over 99%, a total surface area of about 300-350 m²/g, and a pore volume of 1.04 cm³/g with 76% of the pore volume provided by pores having a diameter in the range 7-23 nm.

A series of catalysts was prepared using different modifiers by impregnating the silica with an aqueous solution of the zirconium nitrate, draining, and drying in a rotary evaporator and then in an air oven at 120°C for 2 hours. The impregnation and drying procedure was repeated, if necessary, to obtain the desired modifier content. Cesium was then incorporated by a similar procedure using an aqueous solution of cesium carbonate, to give a cesium content of about 4% by weight (expressed as metal). The catalysts were then calcined in air at 450°C for 3 hours.

The loss of surface area by hydrolysis with time was determined by an accelerated test wherein nitrogen, containing about 40% by volume of water, was passed at a rate of 3 l/h over a 1g sample of the catalyst at 350°C. Periodically the surface area of the samples was determined by a nitrogen adsorption technique after purging with dry nitrogen. The results are shown in the following table.

Example	Zr content (gram atoms per 100 moles of silica)	Surface area (m ² /g) after testing for (days)					
		0	2	5	9	12	18
1 (comparative)	none	307	134	122	102	100	88
2	0.5	316	189	155	-	110	104*
3	1.2	302	208	192	187	183	172
4 (comparative)	2.5	307	240	221	-	200	197*

* after 19 days testing

The catalytic performance of the catalyst samples was determined in an atmospheric pressure microreactor charged with approximately 3 g of catalyst comminuted to 1mm size particles. Before use, the catalyst was dried at 300°C in a 100 ml/min stream of nitrogen for a period of 30 minutes. The catalysts were started-up at 300°C and fed with a mixture of methyl propionate, methanol and formalin. The formalin had a formaldehyde : water : methanol weight ratio of 0.35:0.50:0.15 and the proportions of methyl propionate, methanol and formalin were such that the overall molar proportions of methyl propionate, methanol and formaldehyde were 1:1.45:0.187. The reactants were passed through the catalyst at such a rate that the contact time was initially approximately 5 seconds. After the feed had stabilised (approx. 30 mins), the catalyst temperature was increased to 350°C and left to stabilise overnight. After approximately 16 hours of operation, the catalysts were tested for activity and selectivity by varying the feed gas flow rate. The results are shown in the following table.

Example	Zr content *	Methyl methacrylate plus methacrylic acid - % yield (Y) or % selectivity (S) at residence time of T (sec)											
		T	Y	S	T	Y	S	T	Y	S	T	Y	S
1(comp)	none	1.3	5	94	2.6	8	94	5.5	10	94	8.2	11	92
2	0.5	1.0	4	93	2.0	7	96	5.0	10	93	8.0	11	93
3	1.2	1.2	3	92	2.4	5	94	4.8	9	97	7.0	10	97
4 (comp)	2.5	1.1	3	93	2.2	5	92	4.6	8	90	6.5	10	92

* gram atoms per 100 moles of silica

It is seen that zirconium gave a significant improvement in the retardation of loss of surface area and a significant improvement in selectivity at the longer residence times, except when a relatively large amount of zirconium was employed. The effect on selectivity is also demonstrated by the following table which shows the yield of "heavy" components, i.e. unwanted by products.

Example	Zr content *	Heavies yield (%) at residence time of sec				
		2	3	6	9	19
1 (comp)	none	4	4	7	7	12
2	0.5	1	2	4	5	6
3	1.2	1	1	2	3	4
4 (comp)	2.5	2	3	4	6	8

* gram atoms per 100 moles of silica

Examples 5-7

Catalysts were made and tested as in Examples 1 to 4 but using aluminium nitrate in place of zirconium nitrate. The results are set out in the following tables.

Example	Al content (gram atoms per 100 moles of silica)	Surface area (m ² /g) after testing for (days)					
		0	2	5	9	12	18
1 (comparative)	none	307	134	122	102	100	88
5	0.4	313	220	192	-	160	154*
6	0.7	325	180	-	161**	-	123***
7 (comparative)	2.2	322	288	296	288	283	275

* 19 days, ** 7 days, *** 17 days

Example	Al content *	Methyl methacrylate plus methacrylic acid - % yield (Y) or % selectivity (S) at residence time of T sec								
		T	Y	S	T	Y	S	T	Y	S
1 (comparative)	none	2.6	8	94	5.5	10	94	8.2	11	92
5	0.4	2.4	3	93	4.8	10	94	7.5	12	94
7 (comparative)	2.0	3.0	2	73	6.3	3	75	9.7	4	76

* gram atoms per 100 moles of silica

This illustrates that aluminium is effective as a modifier to increase the stability of the silica,
5 but the use of excessive amounts has an adverse effect upon the activity and selectivity.

Example 8

Example 2 was repeated but using boron oxide dissolved in the cesium carbonate solution in place of zirconium nitrate to give a catalyst containing 0.8 gram atoms of boron per 100 moles of silica. The surface area was 172 m²/g after 6 days testing and thereafter fell slowly, having a value of 157 m²/g after 22 days testing. In the activity testing, at a contact time of 3.8 sec., the yield was 7% and the selectivity was 95%. At a contact time of 6.2 sec., the yield was 9% and the selectivity was 95%.

Example 9

Example 2 was repeated but using a mixture of aluminium nitrate and hafnium oxynitrate in place of zirconium nitrate to give a catalyst containing 0.2 gram atoms of aluminium and 0.3 gram atoms of hafnium per 100 moles of silica. In the activity testing, at a contact time of 3.0 sec., the yield was 7% and the selectivity was 94%. At a contact time of 6.7 sec., the yield was 10% and the selectivity was 94%.

Examples 10-13 (comparative)

Catalysts were made by the procedure of Example 1 using zirconia of 1 mm particle size in place of gel silica as the support. Catalysts were made with nominal cesium contents ranging from 2 to 8% by weight. The results and surface areas of the catalysts are shown in the following table.

Ex.	Cs (%)	Surface area (m ² /g)	Methyl methacrylate + methacrylic acid - % yield (Y) or % selectivity (S) at residence time of T sec					
			T	Y	S	T	Y	S
10	2	93	2.3	6	49	4.7	6	44
11	4	90	2.4	4	38	5.0	4	23
12	6	74	2.5	4	29	5.4	3	15
13	8	73	2.1	2	27	4.4	3	16

The very poor yields and selectivities demonstrate that cesium-doped zirconia is not a suitable catalyst.

Examples 14-16

A series of catalysts were made by the procedure of Example 2, but using a mixture of zirconium nitrate and aluminium nitrate. The results of accelerated hydrolysis and activity testing are shown in the following tables.

Ex	Modifier *		Surface area S (m ² /g) after testing for D days									
	Al	Zr	D	S	D	S	D	S	D	S	D	S
3	0.0	1.2	0	302	2	208	5	192	9	187	12	183
14	0.2	0.3	0	301			6	190	9	183	14	163
15	0.2	0.7	0	285	4	166	7	154	10	143	16	128
16	0.2	1.0	0	308	2	234	5	215			12	190

* g atoms of modifier element per 100 moles of silica

Ex	Modifier *		Methyl methacrylate plus methacrylic acid - % yield (Y) or % selectivity (S) at residence time of T sec								
	Al	Zr	T	Y	S	T	Y	S	T	Y	S
3	0.0	1.2	2.0	5	96				6.6	10	95
14	0.2	0.3	2.5	8	96	3.7	10	95			
15	0.2	0.7	2.6	10	95	3.8	12	94			
16	0.2	1.2	2.1	5	90	4.4	9	91			

* g atoms of modifier element per 100 moles of silica

Examples 17-18

To illustrate that zirconium has a surface area stabilising effect on agglomerated pyrogenic silica, pellets of 3.5 mm diameter and 4 mm length were made by impregnating pyrogenic silica having a purity of over 99%, a total surface area of about 200 m²/g, and a pore volume of 0.8 cm³/g with cesium carbonate and zirconium nitrate to give catalysts containing about 4% by weight of cesium. Surface area testing was effected as in Examples 1-4.

Example	Zr content *	Surface area (m ² /g) after testing for (days)						
		0	2	5	12	16	19	23
17 (comp)	none	148	91	85	70	70	67	64
18	0.7	186	152	151	144	150	144	146

* g atoms per 100 moles of silica

Examples 19-23

Example 18 was repeated using a pyrogenic silica of total surface area about 300 m²/g and pore volume of 0.81 cm³/g to produce catalysts containing various amounts of zirconium and about 4% by weight of cesium. The surface area and activity testing was effected as in Examples 1-4.

Example	Zr content *	Surface area (m ² /g) after testing for (days)						
		0	4	7	11	14	18	21
19	0.5	240	153	153	132	139	-	136
20	0.7	249	169	161	167	149	155	-
21	0.8	246	187	180	180	172	172	175
22	1.0	251	195	171	185	175	176	182

* g atoms per 100 moles of silica

Example	Zr content *	Methyl methacrylate plus methacrylic acid - % yield (Y) or % selectivity (S) at residence time of T sec											
		T	Y	S	T	Y	S	T	Y	S	T	Y	S
19	0.5	1.0	3	89	2.1	5	90	4.4	8	93	7.1	10	92
20	0.7	1.0	3	88	1.9	5	88	4.2	9	91	7.3	11	91
21	0.8	1.1	2	80	2.3	5	81	4.9	9	82	8.6	11	83
22	1.0	1.0	2	64	2.0	4	65	4.2	5	67	7.3	7	68
23(comp)	none	1.2	4	94	2.3	6	93	4.3	8	95	7.0	10	92

* g atoms per 100 moles of silica

Examples 24-26

Example 20 was repeated to give catalysts containing 0.7 gram atoms of zirconium per 100 moles of silica but using different amounts of cesium. The activity of the catalysts was assessed as in Examples 1-4.

Example	Cs (wt%)	Methyl methacrylate plus methacrylic acid - % yield (Y) or % selectivity (S) at residence time of T sec											
		T	Y	S	T	Y	S	T	Y	S	T	Y	S
24	2	1.2	1	31	2.2	2	38	4.6	3	42	11.1	4	45
25	3	1.1	2	73	2.4	4	77	5.0	7	79	11.3	9	80
20	4	1.0	3	88	1.9	5	88	4.2	9	91	7.3	11	91
26	5	1.1	4	89	2.1	7	93	4.2	9	90	10.3	10	88

Catalysts were prepared on the same support as in examples 1-4 but using a different method of catalyst preparation, with 4 wt % caesium and different levels of zirconium. The support was crushed and sieved to a fraction between 0.5 and 2.0 mm. Aluminium nitrate, zirconium nitrate and caesium nitrate were dissolved separately in water. The solutions were mixed and a quantity
 5 equivalent to about 1.5 times the pore volume of the support was added to the support with stirring. This was dried on a hot plate with continuous stirring. The support was then dried at 100°C in air for 3 hours.

The loss of surface area by hydrolysis with time was determined by an accelerated test wherein nitrogen was bubbled through water at 70 °C, thereby containing about 22 % by volume of
 10 water on exit, and then passed at a rate of 60 l/h over a 10g sample of catalyst at 350 °C. At the beginning and the end of the tests the surface area of the samples was determined by a nitrogen adsorption method on a Micromeritics ASAP 2405 nitrogen porosimeter. The results are shown in the table below.

Example	Zr g.atoms/100 g.moles silica	Surface Area at Start (m ² g ⁻¹)	Surface Area after 14 days (m ² g ⁻¹)	Fractional loss of surface area over test
27 (comp)	0.00	273.20	13.10	95
28	0.13	311.20	141.90	54
29	0.26	304.40	189.00	38
30	0.39	303.20	206.90	32
31	0.49	303.90	243.80	20
32	0.66	313.00	228.40	27
33	1.31	311.00	299.00	4

The catalytic performance of the catalysts was tested in a pressurised microreactor charged
 15 with approximately 1g of catalyst. Catalysts were heated to 300 °C for 1 hour in a flow of nitrogen before the reactants-containing stream was introduced in a flow of 25 vol% of a mixture of molar composition methyl propionate : formaldehyde : methanol : water of 1 : 1 : 0.19 : 0.048 and 75 vol% nitrogen at 4 bar absolute, such that the total partial pressure of organics and water was 1 bar absolute. The contact time was adjusted to give about 10% yield where possible. Performances
 20 were measured after 18 hours on stream. The results are shown in the table below and show that catalyst stability towards hydrothermal sintering increases continuously with zirconium content. Catalyst performance is reasonably consistent up to about 0.5g atoms zirconium/100 g.moles silica and declines thereafter. These results indicate an optimum performance combining these two effects at 0.35 to 0.5 g atoms zirconium/100 g.moles silica. Comparison with examples 2-4 shows
 25 that the optimum level is dependent on the method of catalyst preparation.

Example	Zr (g.atoms/100 g.moles silica)	Contact Time (s)	Yield of MMA + MAA	Selectivity to MMA + MAA
27 (comp)	0.00	1.83	10.30	94.06
28	0.13	1.54	10.03	93.36
29	0.26	2.63	12.86	93.81
30	0.39	1.64	7.45	93.79
31	0.49	3.02	10.00	94.14
32	0.66	2.16	10.78	89.84
33	1.31	38.82	3.20	75.84

Examples 34 - 38

Catalysts were prepared on crystalline zirconia powder (surface area $38 \text{ m}^2\text{g}^{-1}$) to which caesium nitrate was added by the method described in Example 28. Catalysts were tested for activity using the method of Example 27. The results are shown in the table below and show that zirconia alone is not a suitable support for MMA synthesis. The best result at 2 wt% caesium was not sustained and after 24 hours running fell to 60% selectivity. Levels of diethyl ketone (DEK), an unwanted by-product of the reaction, are also very high except for the most favourable loading of caesium. DEK is a particular problem at such levels because it has a boiling point which is very close to that of MMA and so it cannot be removed by distillation.

Example	Cs (wt%)	Contact Time (s)	Yield of MMA + MAA	Selectivity to MMA + MAA	DEK yield (% of MMA + MAA)
34	0	10.00	3.09	7.75	32.00
35	2	3.00	9.50	74.80	0.07
36	4	3.00	1.38	2.11	41.00
37	6	52.10	3.04	15.64	27.00
38	8	118.60	1.57	2.65	41.00

10 Examples 39 - 43 (comparative)

Catalysts were prepared by physically mixing the pure silica support used in Examples 1 - 4 ground to 0.6 - 1.0 mm mesh size with portions of the zirconia powder used in Examples 34 - 38 in various proportions. The mixed support was then impregnated with caesium nitrate using the method described in Examples 27 - 33 to give 4 wt% caesium based on weight of silica plus zirconia. The results of catalytic testing and for stability towards hydrothermal sintering using the methods of Examples 27 - 33 are shown in the table below:

Example	Zr content (gatom/100 gmol SiO ₂)	contact time (sec)	Yield of MMA + MAA (%)	selectivity to MMA + MAA (%)	surface area at Start (m ² g ⁻¹)	surface area after 14 days (m ² g ⁻¹)	Fractional loss of surface area over test (%)
39(comp)	0.00	1.83	10.30	94.06	273.2	13.1	95
40(comp)	0.11	1.90	10.46	90.78	304.8	128.3	58
41(comp)	0.45	1.30	11.11	92.74	298.2	133.3	55
42(comp)	2.24	1.30	10.97	91.50	299.3	132.5	56
43(comp)	4.48	2.40	10.51	93.96	269.4	121.4	55

The results show that the presence of zirconium in the form of a physical mixture of zirconia with silica has some beneficial effect upon the loss of surface area after exposure to water and that this effect does not appear to depend upon the amount of zirconia present in the mixture. Zirconium in this form is not, however, as effective as when Zirconium is incorporated into the silica by

- 5 dispersion from solution as demonstrated by Examples 29 - 31. In addition the yield of DEK was considerably greater using the catalysts formed from a mixture of silica and zirconia as shown in the following table.

Example	DEK yield on MMA + MAA (%)
40(comp)	0.15
41(comp)	0.3
42(comp)	0.2
43(comp)	0.14
29	0.02
30	0.02
31	0.01

Examples 44 - 48

- 10 Catalysts were prepared by the method used in Example 28 except that boron oxide was used instead of zirconium nitrate. The catalysts were tested for catalytic performance and stability towards hydrothermal sintering using the method described in that Example and the results are shown below. The beneficial effect of boron on sintering is observed, together with the adverse impact on catalyst performance commencing at above 2 g. atom/100 g atom of silica.

Example	B (g.atom/100 g.atom SiO ₂)	contact Time (sec)	Yield of MMA + MAA (%)	Selectivity to MMA + MAA (%)	Surface area at start (m ² g ⁻¹)	Surface Area after 14 days (m ² g ⁻¹)	Fractional loss of surface area over test (%)
27 (comp)	0.00	1.83	10.30	94.06	273.20	13.10	95.20
44	0.39	1.66	9.50	93.59	311.30	99.60	68.80
45	0.78	5.33	9.97	93.88			
46	1.16	3.02	11.13	94.41			
47	2.00	3.88	11.61	92.05			
48	3.90	5.36	7.48	91.19			

Example 49

A catalyst was prepared by the method in Example 28 but using 0.39 gatom hafnium instead of 0.39 gatom zirconium, hafnium oxynitrate being used instead of zirconium nitrate. The catalyst was tested for stability towards hydrothermal sintering for catalytic activity by the method used in

- 5 Example 27 - 33. The surface area fell from 309 m²g⁻¹ to 125 m²g⁻¹ over the test. At 1.9 second contact time the yield of methyl methacrylate plus methacrylic acid was 10.33% and selectivity was 92.5%.

Example 50

- 10 Catalysts containing caesium and zirconium were prepared on a high purity gel silica in the form of spheres of diameter in the range 2-4 mm having a purity of over 99%, a surface area of 127 m²g⁻¹ by the methods described in Example 28.

Example 51 - 54

Catalysts containing caesium and zirconium were prepared on high purity gel silicas in the form of powders with surface areas as indicated in the table below.

- 15 Example 55 - 58

Catalysts containing caesium and zirconium were prepared on a pyrogenic silica powder with compositions as indicated in the table below.

Example	wt% Cs	gatom Zr/100 gatom SiO ₂	Starting surface area (m ² g ⁻¹)	Surface area after 14 days (m ² g ⁻¹)	% of surface area lost in test
50	4	0.39	127.30	105.40	17
51(comp)	6	-	281.70	113.20	60
52	6	0.39	271.70	174.30	36
53(comp)	6	-	208.00	103.80	50
54	6	0.39	215.20	163.40	24
55(comp)	4	-	226.70	76.90	66
56	4	0.39	264.40	132.40	50
57(comp)	6	-	225.60	59.10	74
58	6	0.39	209.90	66.20	68

Comparison of samples without and with zirconium shows that the improvement in retention of surface area is obtained for all the supports examined.

Examples 59 - 63

Catalysts were prepared using acetate salts instead of nitrate, on the same support as in Examples 1-4. The support was crushed and sieved to a fraction between 0.5 and 2.0 mm. Aluminium hydroxide and caesium hydroxide were dissolved separately in 5% and 10% aqueous acetic acid. A 15% solution of zirconium acetate in aqueous acetic acid (ex Aldrich) was used as received. The solutions were mixed and a quantity equivalent to about 1.5 times the pore volume of the support was added to the support with stirring. This was dried on a hot plate with continuous stirring before being dried for 2 hours at 110C. Catalyst formulations are shown in the table below:

Example	Cs wt%	Zr (g atom/100 gatom of silicon)	Al (g atom/100 gatom of silicon)
59	5	0.33	0.22
60	5	0.66	0
61	5	0.5	0
62	5	0.33	0.44

The catalysts were tested for initial performance and hydrothermal stability by the method described in examples 1-4. The results are shown in the two tables below.

	Methyl methacrylate plus methacrylic acid - % yield (Y) or % selectivity (S) at residence time of T sec														
Example	T	Y	S	T	Y	S	T	Y	S	T	Y	S	T	Y	S
59	1.1	5.1	94.8	2.2	7.5	95.7	2.9	8.8	95.4	5.7	11.2	94.3	8.6	12.8	92.0
60	0.3	5.1	84.6	2.6	7.4	86.3	3.6	9.0	86.6	6.1	10.8	86.5	10.4	11.6	85.8
61	1.2	5.5	91.1	2.4	8.0	91.5	3.3	9.7	91.4	5.5	11.4	90.5	9.5	12.5	87.4
62	1.1	5.1	95.0	2.3	7.4	95.3	3.3	9.0	95.1	5.5	10.9	94.4	8.8	12.5	92.5

	Surface area after n days on line (m^2g^{-1})				
Example	Days on Line	0	7	14	28
59		309	165	112	99
60		296	167	169	158
61		296	142	119	103
62		309	159	132	128

Thus these catalysts display satisfactory catalytic performance and enhanced stability towards sintering of silica compared to Example 1.

Claims

- 1 A catalyst comprising a porous high surface area silica containing 1-10% by weight of an alkali metal (expressed as metal), wherein the catalyst contains a compound of at least one modifier element selected from boron, magnesium, aluminium, zirconium and hafnium in such amount that the catalyst contains a total of 0.25 to 2 gram atoms of said modifier element per 100 moles of silica, said modifier element compound being dispersed in the pores of said silica.
- 2 A catalyst as claimed in claim 1, wherein the surface area of the silica is at least 50 m²g⁻¹.
- 3 A catalyst as claimed in claim 1, wherein at least 50% of the pore volume is provided by pores of diameter in the range 5-150 nm.
- 4 A catalyst as claimed in claim 1, wherein at least 50% of the total surface area of the silica is present in pores of diameter in the range 5-150 nm.
- 5 A catalyst according to claim 1 wherein the alkali metal is cesium.
- 6 A catalyst as claimed in any preceding claim, wherein the compound of at least one modifier element is present in the form of at least one oxide and/or hydroxide of said at least one modifier element.
- 7 A catalyst as claimed in any of the preceding claims wherein the modifier element comprises zirconium and/or aluminium and or borium.
- 8 A catalyst as claimed in any of the preceding claims containing a total of 0.25 to 1.5 gram atoms of said modifier element per 100 moles of silica.
- 9 A method of preparing a catalyst comprising mixing together particles of a porous high surface area silica containing 1-10% by weight of an alkali metal (expressed as metal) with a solution of a compound of a modifier element selected from boron, magnesium, aluminium, zirconium and/or hafnium such that said compound is impregnated into said particles in such amount that the particles contain a total of 0.25 to 2 gram atoms of said modifier element per 100 moles of silica and subsequently drying said particles.

- 10 A method of preparing a catalyst comprising mixing together particles of a porous high surface area silica with a solution of a compound of a modifier element selected from boron, magnesium, aluminium, zirconium and/or hafnium such that said compound is impregnated into said particles in such amount that the particles contain a total of 0.25 to 2 gram atoms of said modifier element per 100 moles of silica; impregnating said particles with a solution of a compound of an alkali metal such that the particles contain 1-10% by weight of said alkali metal (expressed as metal), said impregnation being carried out before during or after the impregnation with the modifier element compound; and subsequently drying said particles.
- 11 A method of preparing a catalyst as claimed in claim 1 comprising co-gelling or co-precipitating a compound of the modifier element with the silica, or hydrolysing a mixture of the modifier element halide with a silicon halide.
- 12 A process for the manufacture of ethylenically unsaturated acids or esters thereof by reaction of an alkanoic acid, or ester of an alkanoic acid, of the formula $R' - CH_2 - COOR$, where R and R' are each, independently, hydrogen or an alkyl group, with formaldehyde in the presence of a catalyst as claimed in any one of claims 1 to 8.
- 13 A process according to claim 12 wherein the ester of the alkanoic acid is methyl propionate and is reacted with formaldehyde in the presence of methanol.
- 14 A process according to claim 12 or claim 13 wherein the formaldehyde is supplied in the form of formalin.
- 15 A process for manufacturing methyl methacrylate comprising reacting methyl propionate with formaldehyde and methanol in the presence of a catalyst comprising a porous high surface area silica containing 1-10% by weight of cesium (expressed as metal), wherein the catalyst contains a zirconium compound in such amount that the catalyst contains a total of 0.25 to 2 gram atoms of zirconium per 100 moles of silica, said zirconium compound being dispersed in the pores of said silica.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/01029

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B01J23/04 B01J21/08 B01J35/10 C07C57/04 C07C51/353
C07C51/347 C07C51/09 C07C67/343 C07C69/54

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01J C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 845 070 A (MONTAG RUTH A) 4 July 1989 (1989-07-04) abstract column 9, line 12 - line 18 column 10, line 68 - column 11, line 2; claims 1,4,6; examples 1,2; table XI	1-8, 11, 12, 14
A	& US 4 990 662 A (HAGEN ET AL) 5 February 1991 (1991-02-05) cited in the application example 1 --- -/--	1-15

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

12 July 1999

Date of mailing of the international search report

27/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Veefkind, V

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/01029

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 933 888 A (SCHLAEFER FRANCIS W) 20 January 1976 (1976-01-20) cited in the application abstract column 2, line 27 - line 33 column 3, line 17 - line 19 column 5, line 21 - line 25 column 5, line 42 - line 47 claims 1,6,12; example 23 -----	1,2, 5-10, 12-15 —
X	EP 0 227 461 A (NIPPON CATALYTIC CHEM IND) 1 July 1987 (1987-07-01) example 13 -----	1,2,6,7
A	Y00 J S: APPLIED CATALYSIS A: GENERAL, vol. 102, 1993, pages 215-232, XP002108650 page 217, line 10 - line 30; tables 1,2 -----	1-8,11, 12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/01029

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4845070 A	04-07-1989	US 4990662 A	05-02-1991
		US 4631264 A	23-12-1986
		US 5241114 A	31-08-1993
		US 4943659 A	24-07-1990
US 3933888 A	20-01-1976	BE 805725 A	05-04-1974
		DE 2349054 A	09-05-1974
		FR 2223080 A	25-10-1974
		GB 1447669 A	25-08-1976
		JP 49070919 A	09-07-1974
		NL 7313562 A	09-04-1974
EP 0227461 A	01-07-1987	JP 1804294 C	26-11-1993
		JP 5013699 B	23-02-1993
		JP 62149337 A	03-07-1987
		JP 1804295 C	26-11-1993
		JP 5013700 B	23-02-1993
		JP 62152539 A	07-07-1987
		AU 591208 B	30-11-1989
		AU 6666486 A	25-06-1987
		CA 1276617 A	20-11-1990
		CN 1014059 B	25-09-1991
		US 4841060 A	20-06-1989